




Tensile Test Specimen (Round)

	Material	D	A (Min)	C (+2)	R (Min)	B (Min)	L (Min)
ASTM A370, E8	Steel	12.5 ± 0.15	60	20	10	50	170
		10 ± 0.1	60	20	4	50	170
		8.75 ± 0.1	45	12	6	40	140
		6.25 ± 0.15	32	10	5	30	120
	SGI	12.5 ± 0.15	60	20	10	50	170
		10 ± 0.1	60	20	4	50	170
		14 ± 0.15	84	20	10	50	200
	CI	20 ± 0.30	60	25	25	50	170
IS 1608-1	Steel	20 ± 0.30	110	25	25	50	-
		14 ± 0.15	77	20	10	50	-
		10 ± 0.1	55	20	10	50	-
		5 ± 0.05	28	10	6	50	-

