




Tensile Test Specimen (Round Sub-size)

Drg. No	D (±0.1)	A (Min)	C (+2)	F (Min)	B (+3)	E (+1)	R (Min)	L (Min)
S125B	12.5	60	18	20	10	32	10	130
S125S	12.5	60	15	25	10	25	10	130
S10S	10	60	20	25	10	32/25	10	130
S875B	8.75	45	11	18	10	18	6	90
S625B	6.25	32	10	12	10	25	5	80
S625S	6.25	32	9	18	10	15	5	80

Data From: ASTM A370-19
IS 1608_1-2018
ISO 6892_1-2016
ASTM E8-2016